

Grease Compatibility

Legend:	Aluminum Complex	Barium	Calcium	Calcium 12-Hydroxy	Calcium Complex	Clay	Lithium	Lithium 12-Hydroxy	Lithium Complex	Polyurea*	Sodium	Calcium Sulphonate	Silica
● Compatible													
▲ Borderline Compatible													
■ Incompatible													
Aluminum Complex	—	■	■	●	■	■	■	■	●	■	■	■	●
Barium	■	—	■	●	■	■	■	■	■	■	■	▲	●
Calcium	■	■	—	●	■	●	●	▲	●	■	■	N/A	N/A
Calcium 12-Hydroxy	●	●	●	—	▲	●	●	●	●	■	■	N/A	N/A
Calcium Complex	■	■	■	▲	—	■	■	■	●	●	■	●	■
Clay (Bentone)	■	■	●	●	■	—	■	■	■	■	■	■	●
Lithium	■	■	●	●	■	■	—	●	●	■	■	●	●
Lithium 12-Hydroxy	■	■	▲	●	■	■	●	—	●	■	■	●	N/A
Lithium Complex	●	■	●	●	●	■	●	●	—	■	■	●	●
Polyurea*	■	■	■	■	●	■	■	■	■	*	■	■	■
Sodium	■	■	■	■	■	■	■	■	■	■	—	■	■
Calcium Sulphonate	■	▲	N/A	N/A	●	■	●	●	●	■	■	—	N/A
Silica	●	●	N/A	N/A	■	●	●	N/A	●	■	■	N/A	—

* Not all polyurea greases are mutually compatible

Greases are not all compatible with each other